

KÖSTER FS-PRIMER 2C

Tehnički podaci / Artikal br J 139 200

Važi od 06.09. 2019.

Vezivno sredstvo-prajmer za KÖSTER Joint Sealant FS-V i FS-H za suve i vlažne podloge

	KÖSTER BAUCHEMIE AG Dieselstraße 1-10, 26607 Aurich 18 J 139 EN 14188-4 Prajmer na bazi smole za hladnju ugradnju
Homogenost Gustina Viskozitet Otpornost na alkale Ponašanje na isparenja Temperatura zapaljivosti	Homogena 1,1 g/cm ³ 400 gr/m ² /s± 15 % Otporan na alkale 1% (60 min, ±1%) 1% (90 min, ±1%) > 160 °C

OPIS

Köster FS – Primer je brzovezujući, transparentni, na bazi razređivača, 1-komponentni agens i ojačivač spojeva, i koristi se kao prajmer pre aplikacije Köster Joint Sealant FS – V i FS – H. Zbog svoje male gustine, penetrira u podlogu nekoliko milimetara, što podlogu čini stabilnijom i čvršćom.

TEHNIČKI PODACI

- Viskoznost niska
- Gustina oko 1.1 g/ cm³ (+ 20°)
- Vreme rada (20°C) oko 20 min
- Temperatura ugradnje od +5 - do +30° C
- Sledeći sloj posle oko 30 min – 3 h

POLJE APLIKACIJE

Vezujući agens za polisulfidne zaptivače spojeva.

PRIPREMA PODLOGE

Podloga mora biti suva, čista, bez silikona, masnoća, kao i bez drugih ostataka nečistoća koje bi mogle da nepovoljno utiču na čvrstinu vezivanja. Preporučujemo da se za čišćenje podloge koristi na vodenoj bazi razređivač, ili čak podlogu ispeskirati, blago oguliti ili očistiti vrelom vodenom parom.

UGRADNJA

FS – Prajmer se nanosi na podlogu parčetom krpice ili valjkom u tankom sloju (potrošnja max. 150 – 250 g/ m²)

Apsolutno je važno ne premašiti preporučenu potrošnju, zbog nepovoljnog uticaja na vreme sazrevanja i jačinu veze. Dozvoliti prajmeru vreme sazrevanja oko 2 – 3 h, mora biti blago lepljiv.

POTROSNJA

oko 10 – 20 gr/ m, Zavisi od podloge

CISCENJE ALATA

Alati se po upotrebi odmah čiste sa Koster Universal Cleanerom

PAKOVANJE

200 ml konzerva. Kombinovano A I B komponente

ZASTITA

Pri radu koristiti rukavice otporne na razređivače kao i ostalu zaštitnu opremu. Obezbediti dobru ventilaciju tokom rada.

SKLADISTE

Skladištiti materijal između +10°C i +25°C. U originalnom pakovanju može biti skladišten 12meseci

POVEZANI PROIZVODI

Koster Joint sealant FS-V	J 231
Koster Joint sealant FS-H	J 232
Koster KD Sistem	W 219
Koster Universal Cleanerom	X 910 010

The accurate and thereby effective and successful application of our products is not subject to our control. The guarantee can therefore only be applied to the quality of our products within the scope of our terms and conditions, not, however, for their effective and successful application. These guidelines replace all previous ones.

Svetosavska 4/3 Zemun tel / fax 2192 286 37 39 234 matični broj 20160705
PIB 104401518, TEKUĆI RAČUN: 205-106366-23 Komercijalna banka ad Bgd
BEST MI-SVE DOO